

Date: 05-13-2019

| | |
|---------------|------------|
| Client | StaticWorx |
|---------------|------------|

| | |
|------------------------------|--|
| Test Method Conducted | ASTM F925 (Regular) Standard Test Method for Resistance to Chemicals of Resilient Flooring |
|------------------------------|--|

| Description of Test Sample | |
|----------------------------|---------------------------------|
| Identification | EC Compound |
| Color | Grey with White and Black Chips |

TEST RESULTS

| STAINING AGENT | 5 Minute Ratings | | | 24 Hour Ratings | | |
|-----------------------|------------------|----------------|--------------|-----------------|----------------|--------------|
| | SURFACE DULLING | SURFACE ATTACK | COLOR CHANGE | SURFACE DULLING | SURFACE ATTACK | COLOR CHANGE |
| 5% Acetic Acid | 0 | 0 | 0 | 0 | 0 | 0 |
| 70% Isopropyl Alcohol | 0 | 0 | 0 | 0 | 0 | 0 |
| Mineral Oil | 0 | 0 | 0 | 0 | 0 | 0 |
| 5% Sodium Hydroxide | 0 | 0 | 1 | 0 | 0 | 1 |
| 5% Hydrochloric Acid | 0 | 0 | 0 | 0 | 0 | 0 |
| 5% Ammonia | 0 | 0 | 0 | 0 | 0 | 0 |
| Bleach | 0 | 0 | 0 | 0 | 0 | 0 |
| 5% Phenol | 0 | 0 | 0 | 0 | 0 | 0 |
| Gasoline | 0 | 0 | 0 | 0 | 0 | 0 |
| Sulfuric Acid | 0 | 0 | 0 | 0 | 0 | 0 |
| Kerosene | 0 | 0 | 0 | 0 | 0 | 0 |
| Olive Oil | 0 | 0 | 0 | 0 | 0 | 0 |

| | |
|--------------------|--|
| Ratings Key | 0 - No change, 1 - Slight change, 2 - Moderate change, 3 - Severe change |
|--------------------|--|