

**Date:** 05-13-2019

<b>Client</b>	StaticWorx
---------------	------------

<b>Test Method Conducted</b>	ASTM F925 (Regular) Standard Test Method for Resistance to Chemicals of Resilient Flooring
------------------------------	--

Description of Test Sample	
<b>Identification</b>	EC Compound
<b>Color</b>	Grey with White and Black Chips

## TEST RESULTS

STAINING AGENT	5 Minute Ratings			24 Hour Ratings		
	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE
5% Acetic Acid	0	0	0	0	0	0
70% Isopropyl Alcohol	0	0	0	0	0	0
Mineral Oil	0	0	0	0	0	0
5% Sodium Hydroxide	0	0	1	0	0	1
5% Hydrochloric Acid	0	0	0	0	0	0
5% Ammonia	0	0	0	0	0	0
Bleach	0	0	0	0	0	0
5% Phenol	0	0	0	0	0	0
Gasoline	0	0	0	0	0	0
Sulfuric Acid	0	0	0	0	0	0
Kerosene	0	0	0	0	0	0
Olive Oil	0	0	0	0	0	0

<b>Ratings Key</b>	0 - No change, 1 - Slight change, 2 - Moderate change, 3 - Severe change
--------------------	--